

Polymer CR/EPDM/SBR

Code

R4261-N

1. DIMENSIONS AND APPEARANCE			
Standard bun size (W x L x T) Color	in in	54 x 80 x 3 42 x 72 x 3 Black	
2. PROPERTIES			
Density	pcf kg/m ³	5 - 7 80 - 112	ASTM D1056 ASTM D1056
Compression deflection (25%)	psi kPa	2 - 5 14 - 34	ASTM D1056 ASTM D1056
Hardness	Shore OO	35 - 55	ASTM D2240
Compression set (50%)	%	50 max.	ASTM D1056
Tensile strength	psi	25 min.	ASTM D412
•	kPa	172 min.	ASTM D412
Elongation	%	90 min.	ASTM D412
Water absorption	%w	10 max.	ASTM D1056
Low service temp	°F	-40	ASTM D1056
High service temp	°F	200	
High intermittent temp	°F	250	
Flammability		PASS	FMVSS 302

3. SPECIFICATIONS

ASTM D1056-14 ASTM D6576-13 UL 94 2A1 Type II, grade A/B, soft HF-1, 1.5 mm and higher