

SPECIFICATION SHEET

Updated Jul-2021 www.RubatexUSA.com

Polymer CR/EPDM/SBR

Code **R4271-N**

Standard bun size (W. v. L. v. T)	in	E4 × 90 × 2	
Standard bun size (W x L x T)	in in	54 x 80 x 3	
Color	in	42 x 72 x 3	
Color		Black	
2. PROPERTIES			
Density	pcf	6 - 8	ASTM D1056
-	kg/m³	96 - 128	ASTM D1056
Compression deflection (25%)	psi	5 - 9	ASTM D1056
	kPa	40 - 62	ASTM D1056
Hardness	Shore OO	45 - 60	ASTM D2240
Compression set (50%)	%	50 max.	ASTM D1056
Tensile strength	psi	40 min.	ASTM D412
-	kPa	275 min.	ASTM D412
Elongation	%	90 min.	ASTM D412
Water absorption	%w	5 max.	ASTM D1056
Low service temp	°F	-40	ASTM D1056
High service temp	°F	200	
High intermittent temp	°F	250	
Flammability		PASS	FMVSS 302

3. SPECIFICATIONS

ASTM D1056-14 ASTM D6576-13 UL 94 2A2

Type II, grade A/B, soft-medium HF-1, 1.5 mm and higher