

SPECIFICATION SHEET

Updated Jun-2022 www.RubatexUSA.com

Polymer CR/EPDM/SBR

Code **R4281-N**

1. DIMENSIONS AND A	PPEARANCE		
Standard bun size (W x L x T) Colour	in	52 x 75 x 2.8 Black	
2. PROPERTIES			
Density	pcf kg/m³	8 - 10 128 - 160	ASTM D1056 ASTM D1056
Compression deflection (25%)	psi kPa	9 - 13 62 - 90	ASTM D1056 ASTM D1056
Hardness	Shore OO	60 - 80	ASTM D2240
Compression set (50%)	%	50 max.	ASTM D1056
Tensile strength	psi kPa	100 min. 689 min.	ASTM D412 ASTM D412
Elongation	%	150 min.	ASTM D412
Water absorption	%w	5 max.	ASTM D1056
Low service temp	°F	-40	ASTM D1056
High service temp	°F	200	
High intermittent temp	°F	250	
Flammability		PASS	UL-94 HF-1